

# YELMINI MARBLE COMPANY

Saint Amour - Jura

## TECHNICAL SPECIFICATIONS

### ■ Blue Savoy : technical Specifications

> density (Kg/m<sup>3</sup>)

~2740

> porosity (%)

~0.2

> sound-speed propagation (m/s)

~5615 to 5930

> coefficient of capillarity

C<sub>2</sub>

g/(m<sup>2</sup>.sec 0.5)

~1.3

> slip

~ 54

> flexion (MPa)

~16.5

> compression (MPa)

~ 157

> abrasion-metallic disk test (mm)

~21.5

> freeze

~ 96 < N < 144 cycles

#### Contact

MARBRERIE YELMINI

Chemin de Carlet

39160 SAINT AMOUR

Tel. +33 (0)3 84 48 73 58

info@yelmini.com